

ZINC-ALUMINIUM (+AZ)

High-strength steels

Hot-coated

Flat-rolled carbon steel products can be coated with special metals or mixtures of metals, to completely avoid or postpone as much as possible the oxidation process of the steel.

These coatings may vary in type and thickness depending on the customer's needs and the impact that a given environmental context may have on the material.

Albasider is able to supply its customers with sheets, strips and strips of hot-coated materials, with thicknesses between 0.4 and 3 mm. Albasider also provides its customers with a wide range of coating types

	Thickness	Width
Plates	0.40 - 3	≤ 2000
Tapes	0.40 - 3	≤ 2000
Straps	0.40 - 3	da 180 a 2000

Coating grades (+AZ)

AZ	AZ 70	AZ 100	AZ 150	AZ 185
Thickness (µm)	9/9	13/13	20/20	25/25

> Zinc-Aluminium (+AZ)

The Zinc-Aluminium coating is composed of an aluminium-zinc alloy (55% aluminium, 1.60% silicon and 43.40% zinc).

The predominant presence of aluminium gives this particular coating:

- high corrosion resistance
- high abrasion resistance
- brilliant surface and excellent reflectance

Surface Finish		Surface Treatment	
Finish	Appearance	C	Passivated
A	Standard	O	Oiled
B	Enhanced	CO	Passivated + Oiled
		S	Anti fingerprint

High-strength steels

Also called micro-alloy steels, in addition to a low carbon content they have a high purity internal molecular structure.

Due to their low carbon content, they exhibit improved weldability.

The ductility, fatigue resistance and formability of these steels offer high performance at a low weight.

Main fields of application:

CONSTRUCTION
AND BUILDING

AGRICULTURAL
MACHINERY

CARPENTRY

PROFILES

AUTOMOTIVE
AND TRANSPORT

Mechanical properties

Thickness (mm)	EN 10346	HX260LAD+AZ	HX300LAD+AZ	HX340LAD+AZ
0.40 - 0.50	Re (Mpa)	260 - 330	300 - 380	340 - 420
	Rm (Mpa)	350 - 430	380 - 480	410 - 510
	A 80 (%)	≥ 20	≥ 17	≥ 15
0.51 - 0.70	Re (Mpa)	260 - 330	300 - 380	340 - 420
	Rm (Mpa)	350 - 430	380 - 480	410 - 510
	A 80 (%)	≥ 22	≥ 19	≥ 17
0.71 - 3	Re (Mpa)	260 - 330	300 - 380	340 - 420
	Rm (Mpa)	350 - 430	380 - 480	410 - 510
	A 80 (%)	≥ 24	≥ 21	≥ 19

Thickness (mm)	HX380LAD+AZ	HX420LAD+AZ	HX460LAD+AZ	HX500LAD+AZ
0.40 - 0.50	380 - 480	420 - 520	460 - 560	500 - 620
	440 - 560	470 - 590	500 - 640	530 - 690
	≥ 13	≥ 11	≥ 9	≥ 7
0.51 - 0.70	380 - 480	420 - 520	460 - 560	500 - 620
	440 - 560	470 - 590	500 - 640	530 - 690
	≥ 15	≥ 13	≥ 11	≥ 9
0.71 - 3	380 - 480	420 - 520	460 - 560	500 - 620
	440 - 560	470 - 590	500 - 640	530 - 690
	≥ 17	≥ 15	≥ 13	≥ 11

Please note: Tests carried out transversely to the rolling direction.