

## GALFAN (+ZA)

## High-strength steels

## Hot-coated

Flat-rolled carbon steel products can be coated with special metals or mixtures of metals, to completely avoid or postpone as much as possible the oxidation process of the steel.

These coatings may vary in type and thickness depending on the customer's needs and the impact that a given environmental context may have on the material.

Albasider is able to supply its customers with sheets, strips and strips of hot-coated materials, with thicknesses between 0.4 and 3 mm. Albasider also provides its customers with a wide range of coating types.

	Thickness	Width
Plates	0.40 - 3	≤ 2000
Tapes	0.40 - 3	≤ 2000
Straps	0.40 - 3	da 180 a 2000

## Coating grades (+ZA)

ZA	ZA 90/40	ZA 95	ZA 130	ZA 155	ZA 185	ZA 200	ZA 255
Spessore (µm)	7/3	7/7	10/10	12/12	14/14	15/15	20/20

## &gt; Galfan (+ZA)

The galfan coating consists of a zinc-aluminium alloy. The composition of the coating is approx. 5% aluminium and approx. 95% zinc.

The presence of aluminium gives this particular coating greater corrosion resistance than galvanised coating, with the same coating thickness.

Surface Finish		Trattamento Superficiale	
Finish	Appearance	C	Passivated
A	Standard	O	Oiled
B	Enhanced	CO	Passivated + Oiled
		S	Anti fingerprint

# High-strength steels

Also called micro-alloy steels, in addition to a low carbon content they have a high purity internal molecular structure.

Due to their low carbon content, they exhibit improved weldability.

The ductility, fatigue resistance and formability of these steels offer high performance at a low weight.

## Main fields of application:

CONSTRUCTION  
AND BUILDING

AGRICULTURAL  
MACHINERY

CARPENTRY

PROFILES

AUTOMOTIVE  
AND TRANSPORT

## Mechanical properties

Thickness (mm)	EN 10346	HX260LAD+ZA	HX300LAD+ZA	HX340LAD+ZA
0.40 - 0.50	Re (Mpa)	260 - 330	300 - 380	340 - 420
	Rm (Mpa)	350 - 430	380 - 480	410 - 510
	A 80 (%)	≥ 22	≥ 19	≥ 17
0.51 - 0.70	Re (Mpa)	260 - 330	300 - 380	340 - 420
	Rm (Mpa)	350 - 430	380 - 480	410 - 510
	A 80 (%)	≥ 24	≥ 21	≥ 19
0.71 - 3	Re (Mpa)	260 - 330	300 - 380	340 - 420
	Rm (Mpa)	350 - 430	380 - 480	410 - 510
	A 80 (%)	≥ 26	≥ 23	≥ 21

Thickness (mm)	HX380LAD+ZA	HX420LAD+ZA	HX460LAD+ZA	HX500LAD+ZA
0.40 - 0.50	380 - 480	420 - 520	460 - 560	500 - 620
	440 - 560	470 - 590	500 - 640	530 - 690
	≥ 15	≥ 13	≥ 11	≥ 9
0.51 - 0.70	380 - 480	420 - 520	460 - 560	500 - 620
	440 - 560	470 - 590	500 - 640	530 - 690
	≥ 17	≥ 15	≥ 13	≥ 11
0.71 - 3	380 - 480	420 - 520	460 - 560	500 - 620
	440 - 560	470 - 590	500 - 640	530 - 690
	≥ 19	≥ 17	≥ 15	≥ 13

**Please note:** Tests carried out transversely to the rolling direction.